

Attribute	Value	Value
Abrasion group	T	class
Dimensional stability	≤ 0,40	%
Curling	≤ 8	mm
Light stability	≥ 6	degree
Residual indentation	≤ 0,35	mm
Impact sound improvement	Δ Lw 21	dB
Dynamic coefficient of friction	> 0,60	
Slip resistance (ramp test with oil)	R10	scale
Reaction to fire	Cfl-s1	class
Report number	VNLF 031380.4	
Underfloor heating	suitable	
Thermal resistance	0,021	m ² .K/W
Thermal conductivity	0,19	W/(m.K)
Chemical resistance	resistant	
Static electrical propensity	< 2kV	on concrete
Pendulum test	39+	
Cold welding	type A	
Intensity of use	23 domestic heavy 31 commercial moderate	class
Total thickness	4,00	mm
Wear layer	0,25	mm
Total weight	2240	g/m ³
Standard width	2 - 3 - 4	m
Standard length	+/- 25	m